

9000-9400 PIGMENTS

| PIGMENT | COLOUR | TYPE OF PIGMENT | COLOUR INDEX | SOLIDS C.A. % | LIGHT FASTNESS 40H | | PVC MIGRATION 80°C | COVERING |
|------------|------------|------------------|--------------|---------------|--------------------|-------------|--------------------|-----------|
| | | | | | FULL SHADE | 5% ON WHITE | | |
| PC 9005 | Red brown | Iron oxide | Red 101 | 27 | 8 | 8 | 5 | Very High |
| PC 9006 | Red | Metallized AZO | Red 48:8 | 13 | 8 | 6 | 3 | Medium |
| PC 9007 | Bordeaux | Metallized AZO | Red 63:1 | 28 | 8 | 3 | 2 | Medium |
| PC 9009 | Ochre | Iron oxide | Yellow 42 | 39 | 8 | 8 | 5 | Very High |
| PC 9010 | Green | Phtalocyanine | Green 7 | 12,5 | 8 | 8 | 5 | Medium |
| PC 9016 | Fuchsia | Naphtol | Red 146 | 13 | 6 | 5 | 4 | Medium |
| PC 9017 | Violet | Dioxazine | Violet 23 | 11 | 8 | 8 | 5 | Medium |
| PC 9055 | Dark Brown | Fe / Mg oxide | Brown 43 | 28 | 8 | 8 | 5 | High |
| PC 9066 | Pink | Quinacridone | Red 122 | 16 | 8 | 8 | 3 - 4 | Medium |
| PC 9073 | Yellow | Dyarilide | Yellow 13 | 27 | 8 | 8 | 3 - 4 | High |
| PC 9074 | Orange | Dinitranilina | Orange 34 | 25 | 8 | 8 | 3 - 4 | Very High |
| PC 9076 | Red | Metallized AZO | Red 48:8 | 41 | 5 | 5 | 4 | Very High |
| PC 9083 | Lemon | Dyarilide | Yellow 83 | 21 | 8 | 8 | 5 | High |
| PC 9125 | Black | Carbon black | Black 7 | 14,5 | 8 | 8 | 4 - 5 | Very High |
| PC 9201 | White | Titanium dioxide | White 6 | 51 | 8 | 8 | 5 | Very High |
| PC 9202 | Black | Carbon black | Black 7 | 13 | 8 | 8 | 5 | Very High |
| PC 9211 | White | Titanium dioxide | White 6 | 51 | 8 | 8 | 5 | Very High |
| PC 9401 | White | Titanium dioxide | White 6 | 51 | 8 | 8 | 5 | Very High |
| | | | | | | | | |
| PC 9005 CS | Red brown | Iron oxide | Red 101 | 53 | 8 | 8 | 5 | Very High |
| PC 9008 CS | Blue | Phtalocyanine | Blue 15:1 | 23,5 | 8 | 8 | 5 | Medium |
| PC 9009 CS | Ochre | Iron oxide | Yellow 42 | 50 | 8 | 8 | 5 | Very High |
| PC 9125 CS | Black | Carbon black | Black 7 | 19 | 8 | 8 | 5 | Very High |

| PIGMENT | COLOUR | TYPE OF PIGMENT | COLOUR INDEX | SOLIDS C.A. % | LIGHT FASTNESS 40H | | PVC MIGRATION 80°C | COVERING |
|-------------------|--------------|-------------------------|----------------|---------------|--------------------|----------|--------------------|------------------|
| PC 9221 CS | White | Titanium dioxide | White 6 | 55 | 8 | 8 | 5 | Very High |